

Decision on

End of Waste Criteria relating to

Recycled Aggregates from Construction and Demolition Wastes for use by

Starrus Eco Holding Limited,

T/A Panda Greenstar,

Ballymount Road Lower,

Dublin 12.

Decision establishing End-of-Waste Criteria

under

Article 28 of the European Communities (Waste Directive) Regulations 2011

For

Recycled Aggregates from Construction and Demolition wastes

produced by Starrus Eco Holding Limited, T/A Panda Greenstar, Ballymount Road Lower, Dublin 12.

ENVIRONMENTAL PROTECTION AGENCY

An Ghníomhaireacht um Chaomhnú Comhshaoil

PO Box 3000, Johnstown Castle, Co. Wexford, Ireland, Y35 W821

Telephone: +353 53 916 0600 Fax: +353 53 916 0699

E-mail: info@epa.ie Website: www.epa.ie

© Environmental Protection Agency 2019

Table of Contents

1.	Introduction & Background	3
2.	Decision and Reasons for the Decision	4
3.	Glossary of Terms	5
4.	End-of-waste criteria	6
5.	Compliance	6
6.	Non-Compliance	6
7.	Waste Inputs & Controls	7
8.	Quality Management System	7
9.	Records	8
10.	Use and Restrictions on Use	10
A	nnex 1: End of Waste Criteria and Monitoring Requirements	11
A	nnex 2: Acceptable Inert Waste Input Materials	18
A	nnex 3: Standards, Specifications, and Quality Controls for the Use of Aggregates	19
A	Innex 4: Sampling and Analysis	20

1. Introduction & Background

- 1.1. Article 6 of the Waste Framework Directive, 2008¹ was transposed into Irish law by the European Communities (Waste Directive) Regulations 2011². The Regulations assign responsibility to the Environmental Protection Agency to make certain decisions regarding end-of-waste. This responsibility is assigned under Article 28(3) and states that the Agency may decide case by case whether certain waste has ceased to be waste.
- 1.2. End-of-waste is a means of determining the point at which, for the purposes of waste regulation, a material need no longer be classified as waste after it has undergone a recovery, including recycling, operation and complies with specific criteria to be developed in accordance with the following conditions:
 - a. the substance or object is commonly used for specific purposes;
 - b. a market or demand exists for such a substance or object;
 - c. the substance or object fulfils the technical requirements for the specific purposes and meets the existing legislation and standards applicable to products; and
 - d. the use of the substance or object will not lead to overall adverse environmental or human health impacts.
- 1.3. The purpose of this document is to set out end-of-waste criteria for the production and use of recycled aggregate from wastes from the construction and demolition sector and waste management facilities. Compliance with these criteria is sufficient to ensure that the recycled aggregate may be used as a secondary raw material without the need for waste regulation or waste controls.
- 1.4. This document indicates how compliance should be demonstrated.
- 1.5. Where the recycled aggregate is produced at a facility authorised by the Environmental Protection Agency (EPA), the EPA is the regulatory authority for overseeing that the recycled aggregate has been produced in accordance with these end-of-waste criteria.
- 1.6. Where the recycled aggregate is produced at a facility authorised by the local authority, the local authority is the regulatory authority for overseeing that the recycled aggregate has been produced in accordance with these end-of-waste criteria.
- 1.7. These end-of-waste criteria are applicable in the Republic of Ireland only. Countries of transit and/or destination may take a different view and these end-of-waste criteria may not be recognised. If the competent authority in the country of transit and/or destination considers the material to be waste, the shipment may, if required by that competent authority, be subject to the controls set out in the Waste Shipment Regulation³.
- 1.8. These end-of-waste criteria may be reviewed and updated by the EPA at any stage based on the experience of practical applications, technological developments or legislative amendments. The EPA reserves the right to depart from the position

¹ Waste Framework Directive - Directive 2008/98/EC on waste (WFD)

² Waste Directive Regulations - European Communities (Waste Directive) Regulations 2011 (SI 126 of 2011)

³ Waste Shipment Regulations - Waste Management (Shipments of Waste) Regulations, 2007 (SI No. 419 of 2007)

outlined and to take appropriate action to avoid overall adverse environmental or human health impacts.

- 1.9. If at any time the European Commission publishes generally applicable end-of-waste criteria for recycled aggregate produced from wastes originating from the construction and demolition sector or waste management facilities, those European criteria may supersede these criteria and the EPA may withdraw this decision.
- 1.10. These criteria do not affect the obligation of producers to hold and comply with a waste collection permit, certificate of registration, waste facility permit or waste/industrial emissions licence or any other National or European legislation which may apply when transporting, storing or processing waste.
- 1.11. These Criteria do not affect permitting or any other legal requirements that do not depend on the status of the material as a waste.

2. Decision and Reasons for the Decision

The EPA has decided, in accordance with article 28(3) of the European Communities (Waste Directive) Regulations 2011, that the recycled aggregate (as defined in section 3 below) the subject of the application made by Beauparc Utilities Limited, on behalf of Panda, Ballymount Road Lower, Dublin 12, on the 8th March 2019 and produced at an authorised waste facility operated by Starrus Eco Holdings Ltd., T/A Panda Greenstar will cease to be waste if it complies with the end-of-waste criteria set out in Section 4 of this document.

The EPA is satisfied, based on:

- the information provided by the applicant, including additional information;
- Standards for the production of aggregate;
- Construction Product Regulation 2011;
- Joint Research Centre, 2009 Final Report on "End-of-waste criteria", and
- Joint Research Centre, 2014 Technical Report on the "Study on methodological aspects regarding limit values for pollutants in aggregates in the context of possible development of end-of-waste criteria under the EU Waste Framework Directive"

that, subject to compliance with the end-of-waste criteria below, the recycled aggregate conforms with the requirements of article 28(1)(a) & (b) of the Regulations and its use as an aggregate will not lead to overall adverse environmental and human health impacts.

3. Glossary of Terms

Aggregate	Granular material of natural, manufactured or recycled origin used in construction.
Applicant	Beauparc Utilities Limited, on behalf of Panda
Attestation Level	A measure of how onerous a system of assessment is required to verify constancy of performance under the Construction Product Regulations (CPR).
Authorised waste facility	A facility which has been granted a waste authorisation in the form of an industrial emissions licence, a waste licence, a waste facility permit or a certificate of registration.
Construction Products Regulations (CPR)	Construction Product Regulations 2013 (S.I. No. 225 of 2013) transposed the EU Regulation No. 305/2011 into Irish Law. The regulation lays down harmonised conditions for the marketing of construction products across Member States of the European Union.
Consignment	Each load of recycled aggregate that leaves the waste facility.
Declaration of Conformity	A declaration that the recycled aggregate conforms to end-of-waste criteria, product standards and specifications, it includes details of restriction on use of the recycled aggregate.
Facility	Any site or premises used for the purpose of the recovery or disposal of waste.
Factory Production Control	A management system focusing mainly on the production process which aims to ensure that product quality is consistently maintained to the required standards and specifications.
Groundwater	Means all water which is below the surface of the ground in the saturation zone and in direct contact with the ground or subsoil.
Inert	As defined in Council Directive 1999/31/EC on the landfill of waste
Producer	Starrus Eco Holdings Ltd., T/A Panda Greenstar
Recovery	As defined in the Waste Management Act 1996 as amended
Recycled aggregate	Aggregate that meets the end-of-waste criteria set out in this document.
Recycling	As defined in the Waste Management Act 1996 as amended
Surface Water	Means inland waters, except groundwater, transitional waters and coastal waters, except in respect of chemical status for which it shall also include territorial waters.
User	User means construction companies, manufacturers, contractors and all those organisations or individuals responsible for the end use of aggregate.
Waste	As defined in the Waste Management Act 1996 as amended

4. End-of-waste criteria

- 4.1.Recycled aggregate shall cease to be waste and no longer subject to waste management controls if, upon transfer from the producer to another person, all the following conditions are fulfilled:
 - a) the waste used as input for the recovery operation complies with the criteria and monitoring requirements set out in Section 1 of Annex 1;
 - b) the inputs have been treated in accordance with the criteria and monitoring requirements set out in Section 2 of Annex 1;
 - c) the recycled aggregate resulting from the recovery operation complies with the criteria and monitoring requirements set out in Section 3 & 4 of Annex 1.

5. Compliance

- 5.1. The recycled aggregate may be deemed to have ceased to be waste when conformance with the end-of-waste criteria set out in Section 4 above is demonstrated, verified and recorded.
- 5.2. The recycled aggregate must require no further processing, for the use for which it is destined at the time it is produced to comply with these criteria.
- 5.3. Use may be in
 - a) unbound applications including sub-base, capping, general fill, and pipe bedding; or
 - b) bound applications including hydraulically bound applications, concrete and asphalt.

The use is restricted to the construction of temporary haul roads at the Boliden Tara Mines Tailing Management Facility, which includes a liner, equivalent to that of a nonhazardous landfill, that will be protective against the risk of pollution of groundwater or surface water.

6. Non-Compliance

- 6.1. Recycled aggregate shall remain classified as waste and subject to waste regulatory controls if:
 - 6.1.1. the recycled aggregate is not compliant with the end-of-waste criteria as set out in Section 4 above;
 - 6.1.2. it is discarded or there is an intention or requirement to discard, for example if it is disposed of;
 - 6.1.3. it is stored indefinitely with little prospect of being used;
 - 6.1.4. it is mixed with other waste materials; or
 - 6.1.5. the producer cannot provide an audit report or the necessary documents demonstrating compliance with the certified quality management system.

Failure to manage waste in accordance with waste regulatory controls is an offence.

7. Waste Inputs & Controls

7.1. Waste Inputs

- 7.1.1. Inputs shall be restricted as set out in Annex 1.
- 7.1.2. A visual inspection⁴ of all waste deliveries and an inspection of the accompanying documentation shall be carried out and documented by qualified staff⁵ who are trained on how to identify input material that does not fulfil the criteria. The procedure for recognising prohibited waste streams shall be documented in the management system.
- 7.1.3. Where non-conforming waste is delivered, it shall be immediately moved to a designated quarantine area and stored pending consignment to an appropriately authorised waste management facility.
- 7.1.4. Waste containing, or which has been contaminated by any substance listed in Annex IV of Regulation (EC) No. 850 of 2004 (on persistent organic pollutants) or asbestos shall be immediately moved to a designated quarantine area and stored pending consignment to an appropriately authorised waste management facility for disposal or recovery in accordance with Annex V, part 1, of the Regulation.

8. Quality Management System

- 8.1. The producer shall implement an environmental management system suitable to ensure the demonstration of compliance with the end-of-waste criteria in Section 4 of this document.
- 8.2. The management system shall include a quality assurance system including factory production controls (as required by the harmonised European Standards (hENs)) that complies with IS EN 13242: "*Aggregates for unbound and hydraulically bound materials for use in civil engineering work and road construction*" and/or IS EN 13285: "*Unbound mixtures Specifications*".
- 8.3. The Factory Production Controls (as required by the hENs), shall include, but are not limited to a set of documented procedures concerning each of the following aspects:
 - 8.3.1. Staff training,
 - 8.3.2. Waste acceptance, to include dealing with non-conforming incoming waste for example rejection of loads, quarantine or disposal,
 - 8.3.3. Waste input materials storage and control, to include checking for deterioration of stockpiled waste inputs,
 - 8.3.4. Monitoring of the treatment processes and techniques, to include the use, control, calibration and maintenance of inspection, measuring and test equipment equipment must be uniquely identified,
 - 8.3.5. Monitoring of the quality of recycled aggregate resulting from the recovery operation,
 - 8.3.6. Monitoring of quality of the product during handling, storage, transport and delivery (including sampling and analysis). The finished product must be identifiable up to the point of sale,

- 8.3.7. Feedback from customers concerning the product quality, and
- 8.3.8. Review and improvement of the management system.
- 8.4. The quality assurance system must be reviewed, approved and certified by an independent third party, as a minimum level 2+ attestation⁶ as referred to in Annex V of the Construction Products Regulation⁷ (CPR), or any other equivalent system shall be applied.
- 8.5.As standards and specifications referred to in this document are subject to review, producers shall ensure they are working to the latest version of any standard or specification.
- 8.6. The producer shall, upon request, provide competent authorities including EPA, the relevant local authorities, National Standards Authority of Ireland (NSAI) and the Health and Safety Authority (HSA) access to the quality management system.

9. Records

- 9.1. In order to demonstrate compliance with these end-of-waste criteria, the producer shall keep and retain the following records and those outlined in Annex 1 to 4 of these criteria for a minimum of five years.
 - 9.1.1. Factory Production Control Manual to include but not limited to:
 - 9.1.1.1. Details of a management representative nominated to have responsibility for ensuring that the Factory Production Control is implemented,
 - 9.1.1.2. Records of periodic management reviews of the Factory Production Control to ensure its continuing suitability and effectiveness,
 - 9.1.1.3. Details of controls in sub-contractors,
 - 9.1.1.4. Inert waste 'acceptance criteria' specific to each site/location. These criteria must be followed at all times and must incorporate:
 - i. All statutory requirements relating to the receipt of incoming waste,
 - ii. Requirements arising from a certificate of registration, waste facility permit or waste licence and the duty of care,
 - iii. A list of the types of waste that are accepted (including list of waste codes),
 - iv. Source/place of origin of the waste,
 - v. Supplier and transporting agent, and
 - vi. Method of acceptance.

⁴ "visual inspection" means inspection of consignments using either or all human senses such as vision, touch and smell and any non-specialised equipment. Visual inspection shall be carried out in such a way that all representative parts of a consignment are covered. This may often best be achieved in the delivery area during loading or unloading and before packing. It may involve manual manipulations such as the opening of containers, other sensorial controls (feel, smell) or the use of appropriate portable sensors.

⁵ Qualified staff is defined as: staff who are qualified by experience or training to monitor and assess the properties of the waste inputs.

⁶ By referring to conformity level 2+ of the Construction Products Regulation, it shall be indicated that the quality system must have been reviewed once by an external body assessing the requirements for this system included in the criteria.

⁷ Construction Products Regulation - Regulation (EU) No. 305/2011 (CPR)

- 9.1.1.5. Records of the visual inspection of every load both on initial receipt and after tipping, to ensure compliance with the acceptance criteria.
- 9.1.1.6. A Method Statement of Production (MSP) that represents the recovery process for the incoming waste. It must contain a description or representation of the production process for each product type including:
 - i. Input materials,
 - ii. Equipment used,
 - iii. Actions undertaken at each stage from acceptance of waste to allocation to product stockpiles, and
 - iv. The aggregates must be produced to a recognised standard and/or specification. The aggregate standard and specification will define the properties and characteristics of the product, as suitable for its application.
- 9.1.1.7. Records of the maintenance of processing equipment and adjustment as necessary during production.
- 9.1.1.8. Records and procedures as outlined in Section 8.3 & 8.4 above.
- 9.2. Declaration of Conformity:
 - 9.2.1. Each consignment of recycled aggregate shall be accompanied by a completed "Declaration of Conformity".
 - 9.2.2. The producer shall retain a copy of each Declaration of Conformity for at least five years.
 - 9.2.3. The Declaration of Conformity may be issued, and copies retained electronically.
 - 9.2.4. The Declaration of Conformity shall state that the recycled aggregate is intended exclusively for use in the construction of temporary haul roads at the Boliden Tara Mines Tailing Management Facility, which includes a liner, equivalent to that of a non-hazardous waste landfill, that will be protective against the risk of pollution of groundwater or surface water.
 - 9.2.5. The Declaration of Conformity shall state that the relevant provisions of REACH⁸, CLP⁹ and CPR regulations have been complied with.
 - 9.2.6. The Declaration of Conformity shall be accompanied by or contain a link to an electronic copy of the safety data sheet for the recycled aggregate.
- 9.3.A register of non-conforming products i.e. a product that does not meet the requirements of these criteria shall be maintained. The register shall contain information as to the reasons for the non-conformance and the manner in which the non-conformance was rectified. The register should also include information on the outlet for the non-conforming product, i.e. re-introduced to the start of the process or disposed of or recovered as waste.

⁸ Registration, Evaluation, Authorisation and Restriction of Chemicals - Regulation 1907/2006/EC (REACH)

⁹ Classification, Labelling and Packaging - Regulation (EC) No 1272/2008 (CLP)

10. Use and Restrictions on Use

- 10.1. As for all aggregates, users of recycled aggregates that are produced in compliance with these criteria shall take full account of any environmental impact resulting from such use.
- 10.2. To comply with these criteria, recycled aggregate must be destined for use in
 - a) unbound applications including sub-base, capping, general fill, and pipe bedding; or
 - b) bound applications including hydraulically bound applications, concrete and asphalt.

The use is restricted to the construction of temporary haul roads at the Boliden Tara Mines Tailing Management Facility, which includes a liner, equivalent to that of a non-hazardous waste landfill, that will be protective against the risk of pollution of groundwater or surface water. Annex 1: End of Waste Criteria and Monitoring Requirements

Criteria		Monitoring requirements
1. W	aste used as input for the recovery operation	
1.1	Inputs shall be restricted to the non-hazardous ¹⁰ list of waste codes as outlined below:	All waste deliveries shall be weighed at the on-site weighbridge and as a minimum the following details recorded;
	17 01 01: concrete	i. date of delivery,
	17 01 02: brick	ii. vehicle registration plate number,iii. hauliers name,
	17 01 03: tiles and ceramics	iv. list of waste code,
	17 01 07: mixtures of concrete, bricks, tiles and ceramics other than those mentioned in 17 01 06	 v. description of the waste, vi. weight of the waste, and vii. source of the waste
	17 05 04: soil and stone	
	17 09 04: mixed construction and demolition wastes other than those mentioned in 17 09 01, 17 09 02 and 17 09 03.	A record of visual inspection, in accordance with the quality management system requirements, including factory production controls, shall be maintained, and as a minimum, the following details recorded;
	19 12 12: other wastes (including mixtures of materials) from mechanical treatment of waste other than those mentioned in 19 12 11. 19 12 12 wastes shall be restricted to those originating from the processing of 17 01 01, 17 01 02, 17 01 03, 17 01 07, 17 05 04 or 17 09 04.	 i. Time and date of the inspection, ii. Name and job title of the person carrying out the inspection, iii. Contents of the delivery, iv. Nature of any contaminants identified, and v. If contaminants are identified, details of the actions taken to
1.2	Hazardous wastes or receptacles used for hazardous wastes shall not be used as an input.	correctly dispose of the non-conforming load(s) and corrective action(s) taken to prevent any such recurrence
1.3	Waste containing, or which has been contaminated by, any substance listed in Annex IV of Regulation (EC) No. 850 of 2004 (on persistent organic pollutants) shall not be accepted as an input material.	An asbestos survey should be undertaken prior to any demolition. Any asbestos or asbestos containing material identified must be segregated and disposed of separately in accordance with National and European legislation. Asbestos and asbestos containing materials are not permitted in the input material
1.4	 Waste to be processed into recycled aggregate shall not contain any of the following substances or materials: i. Asbestos or asbestos containing material, ii. Tar-containing asphalt, iii. Roofing materials, iv. Household waste, or 	in the input material. Records of relevant controls and inspections and training must be maintained for a minimum of 5 years. All reviews and revisions of procedures are to be included in an annex to the most up to date version of that procedure.

¹⁰ The rules as outlined in the List of Waste (LoW) should be consulted when determining if a waste is or is not hazardous. The onus is on landowners, economic operators and persons excavating and transporting the waste material to satisfy themselves that this is the case.

Criteria		Monitoring requirements	
	v. Materials such as plastic, wood, plaster, etc. at levels which may give rise to adverse effects on the environment and the presence of such materials may be detrimental to the quality of the recycled aggregate.	Records shall be legible, identifiable and traceable to the process or product.	
1.5	Waste accepted shall be in accordance with any waste authorisation granted to the waste recovery facility. The Waste Acceptance Procedure shall be amended where necessary to conform with the requirements of any grant of authorisation under the Waste Management Act 1996 as amended.		
1.6	Where non-conforming waste is delivered, this shall be immediately moved to a designated quarantine area and stored pending either return to the supplier, or consignment to an authorised waste management facility.		
2. Tr	eatment processes and techniques		
2.1	Waste used as input shall be kept permanently separate from any other waste.	A procedure for on-site waste storage and processing shall be documented in the environmental and quality management system.	
2.2	All processes (such as sorting, separating, size reducing, cleaning and grading) which are required in order to produce the recycled aggregate shall be completed in accordance with the quality management system, including factory production controls, and	All quality records, including any electronic media shall be stored and maintained in a manner that they are readily retrievable and protected against damage, deterioration or loss. Their retention time and stored location will be not less than 5 years.	
	waste regulatory controls.	All records shall be maintained as appropriate or as deemed useful to the environmental system in order to demonstrate compliance with the relevant standard and for no less than 5 years	
3. Qı	ality of recycled aggregate resulting from the recovery operation	n	
3.1	The customer specification shall, as a minimum, include the requirements of the relevant industrial standard. The recycled aggregate shall comply with all procedures, customer specifications and relevant industry standards for direct use in	The procedure for complying with standards and customer specifications as required by this document shall be documented in the environmental and quality management system.	
		Qualified staff shall verify and document that each consignment complies with the appropriate standards, all procedures and specifications.	
		Records shall detail the specific standards, procedures and specifications which are being applied.	

	 a) unbound applications – including sub-base, cap and pipe bedding; or 	pping, general fill, A quality assurance system in line with Factory Production Controls as outlined in IS EN 13242 shall be available for inspection.
	 b) bound applications – including hydraulically bo concrete and asphalt. The use is restricted to the construction of tempor 	shall be analysed to measure the content and nature of contaminant
	at the Boliden Tara Mines Tailing Management Fac includes a liner, equivalent to that of a non-hazarc landfill, that will be protective against the risk of p	acility, which rous waste The process of determining monitoring frequencies shall be documented as part of the management system and shall be available for auditing.
	groundwater or surface water.	Qualified staff shall carry out and document a visual inspection of each batch of recycled aggregate.
3.2	IS EN 13242 and/or IS EN 13285 as a minimum s production of the recycled aggregate;	shall apply to the The contaminant component content of less than or equal to 1% by mass shall be verified by suitably qualified staff, using a suitable and documented
3.3	The manufacturer shall have a quality assurance that complies with IS EN 13242 and/or IS EN 1328	e system in place method.
	 3.3.1 The quality assurance system must be reviewed and approved by an independent third party and shall be of a minimum of level 2+ attestation as referred to in Annex V of the Construction Products Regulations, or any other equivalent system. 3.3.2 The quality assurance system shall as a minimum include 	and shall be of a audit of the Factory Production Controls, and ii. Completed declaration of conformity. The producer shall maintain documentary evidence, for assessment by the
	 acceptance of wastes for processing in aggregate; 	Into recycleddocumented in the Environmental & Quality Management System (EQMS).Copies of appropriate CE marking shall be maintained.
	 process control to include procedures f control, calibration and maintenance o measuring and test equipment, and 	
	iii. sampling, testing and inspection of the aggregate;	ne recycled
	iv. registration of tests and inspections;	
	v. training of the manufacturer or their e	employees.
3.4	The type of testing for each product; and samp frequency must be appropriate to the end use	

Criter	ia	Monitoring requirements
	aggregates and testing frequencies must comply with the standards and specifications for the recycled aggregate produced.	
3.5	Testing to confirm the contaminant component shall be carried out on each batch.	
3.6	The contaminant component in the recycled aggregate shall be less than or equal to 1% by mass.	
3.7	A declaration of conformity shall be completed for each batch of recycled aggregates produced. The declaration of conformity may be issued in electronic form. The declaration of conformity may not be issued after the recycled aggregates have left the recycling facility.	
3.8	The recycled aggregate shall:	
	i. comply with relevant provisions of the CLP regulation;	
	ii. comply with relevant provisions of the REACH regulation; and	
	iii. comply with relevant provisions of the Construction Products Regulations.	
3.9	Recycled aggregate shall be suitable for use, without further processing, as a raw material in unbound applications (including sub-base, capping, general fill, and pipe bedding) or (bound applications (including hydraulically bound applications, concrete and asphalt). The use is restricted to the construction of temporary haul roads at the Boliden Tara Mines Tailing Management Facility, which includes a liner, equivalent to that of a non-hazardous waste landfill, that will be protective against the risk of pollution of groundwater or surface water.	
3.10	Recycled aggregate shall not be supplied or used for:	
	i. uses which are likely to lead to overall adverse environmental or human health impacts,	
	ii. combustion, including as a fuel or for energy recovery; or	
	iii. reprocessing into materials that are to be used as fuel.	

Criter	ria	Monitoring requirements
	Where appropriate, the recycled aggregate shall conform to CE conformity marking requirements as outlined in the Construction Products Regulations, which apply to all aggregates produced in accordance with harmonised European Aggregates Standards and placed on the market to from July 2013.	
4. Sa	ampling and Analysis	
4.1	Product Safety and Environmental Monitoring including leachate, physical contaminant and pollutant limits for the final product - recycled aggregate shall be completed: see Annex 4 below.	In order to demonstrate that the recycled aggregate does not pose a risk to the environment or human health, the producer shall make available; i. Interpretative reports including lab results,
4.2	Procedures for the use, control, calibration and maintenance of inspection, measuring and test equipment must be set up and followed. Equipment must be uniquely identified.	ii. Details of the test methods utilised,iii. Details of accreditation of the test method, and
4.3	A test plan for production must be defined that includes:	iv. Details of accreditation of laboratory.
	a) types of testing for each product, and	
	b) sampling and testing frequency at every 2,000 tonnes	
	relevant standards and specifications set out testing requirement iated with particular end uses.	
5. Ac	dditional Documentation & Records:	
5.1	Marketability of the Recycled Aggregate If requested, purchasers must be provided with the results from the testing regime undertaken on each product.	 To prove marketability of the recycled aggregate, the producers must maintain delivery documentation for every load of recycled aggregate despatched. This delivery documentation must include: Date of supply, Customer's name and contact details, Product description to aggregates standard and customer specification, The name and contact details of the producer, including the address of the site of production, Quantity supplied by weight / volume, A statement that the product was produced in compliance with these criteria, and

Criteria	Monitoring requirements
	vii. Details of restriction on use.
	These requirements are additional to any statutory record-keeping obligations. However, some records may be used to fulfil both a regulatory obligation and evidence of compliance with these criteria.
	For the purposes of these Criteria, the producer, must:
	i. Keep and retain specified records for a minimum of five years; and
	ii. Make them available for inspection by the regulator as requested.

Annex 2: Acceptable Inert Waste Input Materials

These Criteria only apply to recycled aggregates i.e. a granular material used in the construction of temporary haul roads at the Boliden Tara Mines Tailing Management Facility, which includes a liner, equivalent to that of a non-hazardous landfill, that will be protective against the risk of pollution of groundwater or surface water, which are processed from the non-hazardous list of waste codes as outlined below:

17 01 01: concrete

17 01 02: brick

17 01 03: tiles and ceramics

17 01 07: mixtures of concrete, bricks, tiles and ceramics other than those mentioned in 17 01 06

17 05 04: soil and stone

17 09 04: mixed construction and demolition wastes other than those mentioned in 17 09 01, 17 09 02 and 17 09 03.

19 12 12: other wastes (including mixtures of materials) from mechanical treatment of waste other than those mentioned in 19 12 11. 19 12 12 wastes shall be restricted to those originating from the processing of 17 01 01, 17 01 02, 17 01 03, 17 01 07, 17 05 04 or 17 09 04.

Waste inputs must not contain or be contaminated with dangerous substances described in Commission Decision 2000/532/EC. Incidental quantities of inert physical contaminants (such as soils, peat, clays, silts, wood, plastics, rubber, metal) may be present with the input material but must be removed during the processing of the waste to comply with the constituent requirements of aggregates in IS EN Standards and these Criteria.

Annex 3: Standards, Specifications, and Quality Controls for the Use of Aggregates

The producer must comply with all the requirements of a harmonised IS EN aggregates standard appropriate to the use for which the aggregate is destined for, at the time it is produced, to comply with these Criteria. The table below details the product and end uses, the IS EN Standards, specifications and quality controls relating to the production of the aggregate.

IS EN Standard	Specification	Quality Controls
IS EN 13242: Aggregates for unbound and hydraulically bound materials for use in civil engineering work and road construction	As required by the customer	Independent Audit of the Factory Production Controls
IS EN 13242: Aggregates for unbound and hydraulically bound materials for use in civil engineering work and road construction	As required by the customer IS EN 13285: Unbound Mixtures: Specifications	Independent Audit of the Factory Production Controls
IS EN 13242: Aggregates for unbound and hydraulically bound materials for use in civil engineering work and road construction	As required by the customer IS EN 14227-1 to 5 Hydraulically Bound Mixtures: Specifications	Independent Audit of the Factory Production Controls

Should any of the above standards be amended or replaced, the most recent version of the standard shall be complied with, it is the responsibility of the producer and users to ensure that the most up to date version is being considered.

The National Standards Authority of Ireland (NSAI) publishes guidance documents that explain how the European Aggregate Standards are applied in Ireland: the one relevant to Table B1 is SR 21: *Guidance on the use of IS EN 13242:2002+A1:2007 - Aggregates for Unbound and Hydraulically Bound Materials for use in Civil Engineering Work and Road Construction.*

Annex 4: Sampling and Analysis

Procedures for the use, control, calibration and maintenance of inspection, measuring and test equipment must be set up and followed. Equipment must be uniquely identified.

A test plan for production must be defined that includes:

- a) The types of testing for each product,
- b) And sampling and testing frequency.

The relevant standards and specifications set out testing requirement associated with particular end uses. The leachate analysis for parameters outline in the table below should be carried out at a frequency of one per 2,000 tonnes.

Leachate, Physical Contaminant and Pollutant limits for the final product, recycled aggregates:

Parameter	Pollutant Threshold	Unit
Antimony	0.06	mg/kg
Arsenic	0.5	mg/kg
Barium	20	mg/kg
Cadmium	0.04	mg/kg
Chromium	10	mg/kg
Copper	2	mg/kg
Lead	0.5	mg/kg
Molybdenum	0.5	mg/kg
Nickel	0.4	mg/kg
Selenium	0.1	mg/kg
Zinc	4	mg/kg
Mercury	0.01	mg/kg
Phenol	1	mg/kg
Fluoride	10	mg/kg
Chloride	800	mg/kg
Sulphate	20,000	mg/kg
DOC	500	mg/kg
рН	13	pH Units
TDS	60,000	mg/kg
TOC	3	%
Benzene	6	mg/kg
Toluene	6	mg/kg
Ethylbenzene	6	mg/kg
m/p-xylene	6	mg/kg
o-xylene	6	mg/kg
PCB Total of 7	1	mg/kg
Total 17 PAHs	100	mg/kg
Mineral Oil	500	mg/kg
Metal including steel	1%	By mass
Soil	1%	By mass
Gypsum	1%	By mass
Wood	1%	By mass
Plastic	1%	By mass
Rubber	1%	By mass